

FINISHING GROUP S.R.L.

HIGH POWDER TAPE HPT

Backing:	transp. polyester film
Adhesive:	green silicone
Adhesive thickness:	crosslinked 0,04 mm.
Polyester thickness:	0,05 mm.
Total lenght:	55 mt.
Peel on steel (EN 1939)	6,75N/25 mm.
R.B.T. open side (P.S.T.C. PSTC 6)	2,5 cm.
Quick stick on steel open side	5,75N/25 mm.
Shear on steel open side (EN 1943)	100 hours
Temperature range	-51 a +204°C for 60'
Breaking strenght longitude ASTM D882	6,62 kg/mm ²
Breaking strenght trasversal ASTM D882	7,13 kg/mm ²
Elongation on longitude breaking ASTM D882	70%
Elongation on trasversal breaking ASTM D882	80%

NOTE: our recommendations are made in good faith and are based on our experience with this product. Since the conditions of use of this product are beyond our control, this data is given on the express condition and understanding that Finishing Group s.r.l. will not be liabile to any person by reason thereof. Nothing herein shall be deemed to be a recommendation to use any product in violation of any existing patent right.